

TECHNICAL SPECIFICATION

Property	Reference Standard	Units	Nominal Value		
Basis Weight	ISO 536	g/m ²	180	240	280
Taber Stiffness	MD	mN.m	3.0	7.0	12.0
	CD		1.5	3.0	4.5
Thickness	ISO 534	μm	230	310	370
Burst Index	ISO 2758	KPa.m ² /g	3.5	2.5	2.5
Moisture content	ISO 287	%	7.5	7.5	7.5

MD—Machine Direction; CD- Cross-Machine Direction;

Shade

DE* ≤ 2.0

DL*, Da*, Db* -1.5 ≤ DL*, Da*, Db* ≤ 1.5

PRODUCT SPECIFICATION

Basis Weight (g/m ²)	Size (cm)	Packets per pallet	Reams per pallet	Sheets per pack
180	77x110	50	10	100
	110x77	50	10	100
	70x100	50	10	100
240	77x110	40	8	100
	110x77	40	8	100
	70x100	40	8	100
280	77x110	35	7	100
	110x77	35	7	100
	70x100	35	7	100

Mill certifications



PEFC™ certified
This product is from sustainably managed forest and controlled sources.



By buying products with the FSC® label you are supporting the growth of responsible forest management worldwide.