

## TECHNICAL SPECIFICATION

Property		Reference Standard	Units	Nominal Value							
Basis Weight		ISO 536	g/m <sup>2</sup>	135	150	170	190	225	250	300	350
Taber Stiffness	MD	ISO 2493	mN.m	1.0	1.8	2.0	3.0	4.5	5.0	7.0	11.5
	CD			0.5	0.9	1.0	1.5	2.2	2.5	3.2	5.5
Thickness		ISO 534	μm	155	175	200	220	260	290	335	385
Bekk Smoothness		ISO 5627	s	35	27	23	23	23	23	23	23
Moisture Content		ISO 287	%	7.5	7.5	7.5	7.5	7.5	7.5	7.5	7.5
CIE Whiteness		ISO 11475	%	163	163	163	163	163	163	163	163

MD-Machine Direction; CD-Cross-Machine Direction

### Mill certifications



### Product certifications available



PEFC™ certified  
This product is from  
sustainably managed  
forest and controlled  
sources.



By buying products with  
the FSC® label you are  
supporting the growth of  
responsible forest  
management worldwide.

[www.papeldoprado.com](http://www.papeldoprado.com)