

TECHNICAL SPECIFICATION

Property		Reference Standard	Units	Nominal Value								
				135	150	170	190	225	250	300	350	400
Basis Weight		ISO 536	g/m ²	135	150	170	190	225	250	300	350	400
Taber Stiffness	MD	ISO 2493	mN.m	1.0	1.8	2.0	3.0	4.5	5.0	7.0	11.5	17.5
	CD			0.5	0.9	1.0	1.5	2.2	2.5	3.2	5.5	7.0
Thickness		ISO 534	µm	155	175	200	220	260	290	335	385	440
Bekk Smoothness		ISO 5627	s	35	27	23	23	23	23	23	23	23
Moisture Content		ISO 287	%	7.5	7.5	7.5	7.5	7.5	7.5	7.5	7.5	7.5
CIE Whiteness		ISO 11475	%	163	163	163	163	163	163	163	163	163

MD-Machine Direction; CD-Cross-Machine Direction

PRODUCT SPECIFICATION

Substance (g/m ²)	Size (cm)	Packets per pallet	Reams per pallet	Sheets per pack
135	65x92	28	14	250
	70x102	28	14	
150	65x92	24	12	250
	70x102	24	12	
170	65x92	40	10	125
	70x102	40	10	
190	65x92	36	9	125
	70x102	36	9	
225	65x92	32	8	125
	70x102	32	8	
250	65x92	28	7	125
	70x102	28	7	
300	65x92	30	6	100
	70x102	30	6	
350	65x92	25	5	100
	70x102	25	5	
400	70x102	25	5	100

Product certifications available



EU Ecolabel: PT/011/003



www.papeldoprado.com